



Scotch-Grip™

1099 Vinyl Adhesive

Product Data Sheet

Updated : November 1997
Supersedes : March 1996

Product Description

A fast drying adhesive with good resistance to plasticiser migration. Air dried bonds have high strength, resist weathering, water, oil and most solvents.

Excellent for bonding vinyl extrusions and sheeting. Also bonds fabrics, foam and flexible plastics.

Physical Properties

Not for specification purposes

Base	Nitrile Rubber	
Solvent	Acetone	
Flash Point of Solvent	-15°C	
Consistency	Medium Syrup	
Density	0.88	
Viscosity (26°C A3 V10 Brookfield RVF)	2500 cps	
Colour	Light Tan	
Shelf Life	15 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics

Not for specification purposes

180° Peel Strength

Canvas/Aluminium
3M test method C4013.
C4013 : speed of pulling :
50mm/min.

Following values have been measured on 1 lot.

TIME	TEST METHOD	RESULTS (daN/cm)
1 hour at 24°C	C4013 e	1.08
96 hours at 24°C	C4013 e	5.28
72 hours at 24°C + 24 hours in water.	C4013 f	5.80

Date : November 1997
1099 Vinyl Adhesive

Performance Characteristics (Cont...)

Not for specification purposes

Guide Line

180° Peel Strength
Canvas/Steel

TIME	TEMP. TEST	VALUE (daN/cm)
1 day	24°C	1.4
3 days	24°C	3.1
5 days	24°C	3.2
7 days	24°C	2.4
2 weeks	24°C	2.3
3 weeks	24°C	2.1
3 weeks	-34°C	3.8
3 weeks	65°C	1.4
3 weeks	82°C	0.5

Directions for Use

Surface Preparation:

Surfaces must be clean, dry and free from oil or greasy film.

Application:

Stir well before using. With a stiff, short bristled brush or other spreading method, apply a thin even coat to one or both mating surfaces. Coating both surfaces is generally advisable because it gives greater strength and permits a longer open time before bonding. Porous surfaces may require more than one coat to ensure that enough remains on the surface. Allow the adhesive to dry to an aggressively tacky stage where it will adhere, but there is no transfer to the finger when touched lightly. Since Scotch-Grip 1099 adhesive dries rapidly, this open time is rather short. Press or roll surfaces firmly together to ensure good contact at all points. Bonds have considerable strength immediately after joining. Development of ultimate strengths depends largely upon porosity of surfaces being bonded and how soon after joining they permit complete release of the solvent.

Ultimate strengths may be obtained sooner by either of the following reactivation methods. Reactivation is usually advisable where large areas are involved because the adhesive dries rapidly and may result in a poor bond when using the open time method. Reactivation is particularly useful where small areas at a time can be bonded.

Solvent Reactivation:

Allow adhesive to dry completely. Wipe adhesive film rapidly with a cloth moistened in either ketone or ester type solvent and complete bond in the regular manner. If coated areas are kept clean, films of 1099 may be solvent reactivated up to six months after application.

Heat Reactivation:

Allow adhesive to air dry completely. Join surfaces and heat in an oven, press, or under lamps at 120°C to 150°C. Allowance must be made for transfer of heat through mating parts to the adhesive film.

Enough pressure should be applied during heating to ensure intimate contact.

If desired, to obtain superior properties, heat cure the adhesive as shown in the table below, after making the bond as above.

Coverage:

Approx 10m²/litre for a medium brush application (0.025mm dry film).

Bonding Range:

Up to 10 minutes for a one surface application.
Up to 50 minutes for a two surface application.
0.25mm wet film at 25°C.

Application Temperature Range:

16°C to 27°C.

Clean Up:

Excess adhesive may be removed with methyl ethyl ketone, acetone or 3M Industrial Cleaner. When using solvent for clean-up, it is essential that proper precautionary measures for handling such materials are observed.

Temperature of Adhesive Film	Time for Minimum Cure
93°C	120 minutes
116°C	40 minutes
138°C	12 minutes
160°C	8 minutes
182°C	5 minutes
204°C	2 minutes

Date : November 1997
1099 Vinyl Adhesive

Applications	Light colour and plasticiser resistance make 1099 adhesive particularly suitable for plastic bonding. Typical applications and end uses are:	Bonding of ABS parts for appliances, automotive interior panels. Bonding of phenolic resins used in electrical equipment, circuit boards.	Bonding of vinyl polymers/ copolymers used in piping, sheet panels, packaging. Bonding of leathers, urethane foam, rubbers and a variety of plastic on metal, wood and hardboards.
Storage Conditions	Store product between 15°C and 27°C for maximum storage life.		
Health and Safety Information	Precautions: Highly flammable. May cause eye irritation. Keep product and its vapours away from heat and open flames. No smoking. The vapours given off from this product will burn. Take precautionary measures against static discharges. Avoid prolonged breathing of vapours. Use only in well ventilated areas with enough air movement to remove vapours and prevent vapour build up above allowable limits. Avoid eye contact and prolonged or repeated contact with the skin.	First Aid: Eye Contact: Immediately flush with plenty of water and seek medical advice. Skin Contact: Wash immediately with soap and water. Keep container closed when not in use. Keep out of reach of children.	For further Health and Safety information, please contact the Toxicology Department at Bracknell Technical Centre on (01344) 860678.
Specifications	Meets the requirements of: MMM-a-189 C Class 2. AFS 87C. DTD 900/4698		

3M and Scotch-Grip are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Specialty Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC
3M House,
28 Great Jackson Street,
Manchester,
M15 4PA

Customer Service :

Tel 0161 236 8500
Fax 0161 237 1105

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :

Tel (01) 280 3555
Fax (01) 280 3509