



4611F Acrylic Foam Tape

Product Data Sheet

Updated : March 1997
Supersedes : December 1995

Product Description 4611F is a dark grey double coated acrylic foam tape with a high tack acrylic adhesive. This tape has a plain white filmic liner.

Physical Properties
Not for specification purposes

Adhesive Type	Acrylic	3M ref :
Foam Core	Acrylic	Foam Density 840 kg/m ³
Thickness (ASTM D-3652) Tape	1.1 mm ± 0.1mm	
Release Liner	White Filmic	
Tape Colour	Dark Grey	
Foam Density	840 kg/m ³	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics
Not for specification purposes

Peel Adhesion to Stainless Steel 90° peel @ room temp, 72 hr dwell, jaw speed 300mm/min AFERA 4001 (modified)	32 N/10mm	
Static Shear Strength weight held for 100 hours to stainless steel with ½ sq in (3.23 sq cm) overlap	1000g @ 20°C 500g @ 70°C	
Temperature Performance Continuous Intermittent	90 °C 150 °C	

Date : March 1997
4611F Acrylic Foam Tape

Additional Product Information

This product is suitable for plasticised PVC but is not suitable for low surface energy plastics.

Application Techniques

1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.

2. To obtain optimum adhesion, the bonding

surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol & water. Use proper safety precautions for handling solvents.

3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F).

Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.

Applications

4611F is a high performance double coated acrylic foam product which possesses a good balance between shear peel and high tack adhesion. It has been designed to be suitable for a range of bonding applications which require a level of adhesion higher than standard double coated foam tapes but perhaps lower than higher performance 3M VHB™ tapes.

Typical applications include:

- Bonding roof bows on trucks and buses.
- Bonding lower weight glazing (muntin) bars or muntin bars positioned internally.
- Lower weight signage applications.

3M and VHB are trademarks of the 3M Company

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Specialty Tapes & Adhesives

3M United Kingdom PLC
3M House,
28 Great Jackson Street,
Manchester,
M15 4PA

Customer Service :
Tel 0161 236 8500
Fax 0161 237 1105

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509

© 3M United Kingdom PLC 1996