

Issue number 1

Issued October 2004

**ATTG2233 REINFORCED PERM/PEEL
ARCYLIC TRANSFER ADHESIVE**

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

| | | | |
|---|-----------------|-------------|--------|
| Thickness, adhesive plus carrier | | 0.060 | mm |
| Thickness, release liner | | 0.065 | mm |
| Peel adhesion to steel: | Open side | 500 | N/m |
| | Liner side | 160 | N/m |
| Polyester loop tack: | Open side | 600 | N/m |
| | Liner side | 240 | N/m |
| Static shear adhesion, | 1Kg at 23 Deg.C | 30 | Hours |
| Liner release | | 10 | N/m |
| Service temperature range | | -10 to +100 | Deg. C |
| Recommended application temperature range | | +5 to +25 | Deg. C |
| Shelf life | | 12 | Months |
| Test Methods: | BS 7116 | | |

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.

Tel: +44 (0) 1213776070 Fax: + 44 (0) 121 3777175

www.genfab.co.uk Email: info@genfab.co.uk

General Fabrications Ltd, Orphanage Road, Erdington, Birmingham, B24 9HT
Registered in England No. 453031