3M 904 (ATG Version) Transfer Tape

Product Data Sheet

Updated : February 1996 Supersedes : July 1994

Product Description

General purpose clear acrylic adhesive Transfer Tape on white polycoated paper liner, with good temperature performance.

Physical Properties			
Not for specification purposes			

Adhesive Type		3M ref :	
Thickness (ASTM D-3652)			
Таре	0.05 mm		
Liner	0.10 mm		
Total	0.15 mm		
Release Liner	White Polycoated Silicone		
	Paper		
Tape Colour	Clear		
-			
Shelf Life	12 months from date of despatch by 3M when stored in the		
	original carton at 21°C (70°F) & 50% Relative Humidity.		

Performance Characteristics Not for specification purposes	Adhesion to Stainless Steel ASTM D-3330	904 adheres well to most high energy surfaces and plastic materials (ABS, PP, etc). Well suited for bonding a wide variety of similar or dissimilar materials.
	Solvent Resistance	Relative high solvent resistance
	Temperature Resistance	Relative high temperature operating range. Continuous exposure: 120°C. Short term: 200°C. (up to 240°C for minutes).
	UV Light Resistance	Excellent UV resistance
	Peel Adhesion (AFERA 4001)	5 N/10 mm.

Date : February 1996 904 (ATG Version) Transfer Tape

Application Techniques	 Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane. Use proper safety precautions for handling solvent. 	 3. ATG System is the cleaner, easier, more precise way to lay down a strip of 904 adhesive transfer tape. 4. Ideal tape application temperature range is 20°C to 40°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.
Applications	Web splicing (paper, foil, film, fabrics. Core starting. Miscellaneous joining and holding where high initial	Foams, pictures, posters, etc. laminations.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Specialty Tapes & Adhesives

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA Customer Service :

adhesion and long ageing

bond is required.

Tel 0161 236 8500 Fax 0161 237 1105 3M Ireland 3M House, Adelphi Centre, Upper Georges Street, Dun Laoghaire,Co. Dublin, Ireland © 3M United Kingdom PLC 1996

Customer Service :

Tel (01) 280 3555 Fax (01) 280 3509