

AUHB06 Product datasheet

Date: October 2014

Product Overview	High Bond acrylic Foam tape, for a variety of automotive applications and especially on LSE substrates (ceramics / silicones). Very Good Shear. Excellent UV and solvent Resistance Foam Density: 600 kg/m3		
Liner	Red PE Film (paper liner is available)		
Colour	Black		
Range of Applications	General Automotive high bond applications. TL52018 approval		

Test Characteristic	Units	Standard Values	Tolerance	Test Method
Total Thickness (no liner)	mm	0.6	+/- 10%	
Temperature Resistance		90°C long term, 120°C Short term Min temperature -40°C		
90° Peel Adhesion to steel	N/cm	29		ASTMD3330
Static Shear	kpa	880		ASTM 3654

Figures shown refer to average values only, based on tests carried out in laboratory conditions and are not valid for specification. The company reserves the right to modify or change the product at any time without notice.

All information has to be intended as generic advice for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions

Tel: +44 (0) 1213776070 Fax: + 44 (0) 121 3777175

www.genfab.co.uk Email: info@genfab.co.uk General Fabrications Ltd, Orphanage Road, Erdington, Birmingham, B24 9HT Registered in England No. 453031