



# Scotch-Mount™

## 4664 Double Coated Foam Tape

---

### Product Data Sheet

---

Updated : January 1994  
Supersedes :

---

#### Product Description

A-20 is a firm acrylic pressure sensitive adhesive system. It features high ultimate bond strength, very high temperature and solvent resistance and

excellent shear holding power.  
Bond strength increases substantially with time.

---

#### Physical Properties

Not for specification purposes

<b>Adhesive Type</b>	Acrylic	<b>3M ref</b> : A-20
<b>Thickness</b> (ASTM D-3652) Tape Liner Total	0.40 mm 0.08 mm 0.48 mm	
<b>Release Liner</b>	Green Plaid Paper	
<b>Tape Colour</b>	White	
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

---

#### Performance

##### Characteristics

Not for specification purposes

<b>Peel Adhesion to Stainless Steel</b> 90° peel @ room temp, 72 hr dwell, jaw speed 300mm/min.	24 N/10mm	
<b>Static Shear Strength</b> weight held for 10 hours to stainless steel with ½ sq in (3.23 sq cm) overlap	1500 g @ 20°C	
<b>Temperature Performance</b> Max (hours/minutes) Max Continuous (days/weeks)	150°C 100°C	
<b>Normal Tensile (T-Block)</b> to Aluminium at room temp, 6.45 sq cm, jaw speed 50 mm/min	46 N/cm²	
<b>Solvent Resistance</b>	No apparent degradation when exposed to splash testing of most hydrocarbon solvents.	
<b>UV Light Resistance</b>	No apparent degradation when exposed to 7 days in U. V. Chamber.	

Date : January 1994  
4664 Double Coated Foam  
Tape

### Application Techniques

1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.

2. To obtain optimum adhesion, the bonding

surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol. Use proper safety precautions for handling solvents.

3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F).

Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.

### Applications

4664 has been developed to provide high peel and shear performance bonds to a variety of substrates. Its acrylic construction also allows for good sealing capabilities and high temperature performance.

Its superior shear performance makes it ideally suitable for mirror mounting and nameplate bonding applications. Care should be taken to avoid bonding to safety backed mirrors and low surface energy substrates.

**It is suggested that a minimum of 25cm<sup>2</sup> of tape contact on each surface is used to support 1kg of continuous static shear load, however, this should be tested and thoroughly evaluated to ensure it meets specific requirements prior to use.**

3M and Scotch-Mount are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



### Specialty Tapes & Adhesives

3M United Kingdom PLC  
3M House,  
28 Great Jackson Street,  
Manchester,  
M15 4PA

Customer Service :  
Tel 0161 236 8500  
Fax 0161 237 1105

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509

© 3M United Kingdom PLC 1996