

| | |
|-------------------------------|------------------------------------------------------------------------------------------------------------|
| Product | High performance automotive masking tape. |
| Backing | Saturated Buff Crepe paper |
| Adhesive | Solvent Rubber Resin |
| Range of Applications | Designed for automotive refinish use during high temperature drying cycles suited for all types of paints. |
| Temperature resistance | 110°C (60 mins) |

| Test Characteristic | Units | Standard Values | Tolerance | Test Method |
|----------------------------|------------------|-----------------|-----------|-------------|
| Total Weight (no liner) | g/m ² | 110 | +/- 8% | ISO536 |
| Total Thickness (no liner) | µm | 140 | +/- 10% | AFERA5006 |
| MD Tensile Strength | N/cm | >34 | | AFERA5004 |
| MD Elongation at Break | % | >9 | | AFERA5004 |
| Adhesion to steel | N/cm | >2.2 | | AFERA5001 |

Figures shown refer to average values only, based on tests carried out in laboratory conditions and are not valid for specification. The company reserves the right to modify or change the product at any time without notice.

All information has to be intended as generic advice for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions