

Issue No. 1

Issued March 2005

TIR019 HIGH PERFORMANCE DOUBLE-SIDED TISSUE TAPE

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Thickness, adhesive + carrier	0.130	mm
Release liner thickness	0.060	
180 degree peel adhesion: Open side	1500	N/m
Closed side	1500	N/m
Polyester loop tack: Open side	1200	N/m
Closed side	1200	N/m
Liner release	20	N/m
Tensile strength	1000	N/m
Elongation at break	4	%
Service temperature	-40 to +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	100	Hours
Shelf life	12	Months

Test Methods: BS 7116

The individual ingredients of the adhesive have been tested and approved for indirect food contact to the FDA specification 175.105

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.

Tel: +44 (0) 1213776070 Fax: + 44 (0) 121 3777175

www.genfab.co.uk Email: info@genfab.co.uk

General Fabrications Ltd, Orphanage Road, Erdington, Birmingham, B24 9HT
Registered in England No. 453031