

Product datasheet Issue No 2 Issued Jan 2004

**TRA 037 TRANSFER TAPE
MODIFIED ACRYLIC ADHESIVE**

<u>TECHNICAL DETAILS</u>		<u>TYPICAL VALUE</u>	<u>UNITS</u>
Adhesive thickness		0.030	mm
Release liner type		90g Amber glassine	
Release liner thickness		0.075	mm
180 degree peel adhesion:	Open side	650	N/m
			N/m
Polyester loop tack:	Open side	800	N/m
			N/m
Liner release		10	N/m
Tensile strength		N/A	N/m
Elongation at break		N/A	%
Service temperature		-20 to +120	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		20	Hours
Shelf life		12	Months
Test Methods: BS 7116			

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.

Tel: +44 (0) 1213776070 Fax: + 44 (0) 121 3777175

www.genfab.co.uk Email: info@genfab.co.uk

General Fabrications Ltd, Orphanage Road, Erdington, Birmingham, B24 9HT
Registered in England No. 453031